

Floor Sealer Plus

Floor sealer/finish

Description

FLOOR SEALER PLUS creates a new standard of performance for water emulsion floor finishes. It combines the toughness of permanent type finishes with the ease of application and removability of water emulsion finishes. Gloss and durability are unequalled and the expense of buying and applying a sealer is eliminated thus reducing labour costs. One coat covers like two coats of ordinary finish and the ease of application is amazing for this ultra-high solids emulsion. The tough film resists scuffs marks and can be used without buffing, yet shows an immediate response when enhanced by buffing, spray buffing or high speed burnishing.

Features and Benefits

- Works on most hard floor surfaces including: terrazzo, marble, vinyl, timber, concrete, slate, terracotta, asphalt tile, rubber, etc. Not recommended for outdoor use. Designed for high traffic areas.
- High solids 32% resulting in maximum durability. Requires fewer coats saving time and labour
- Anti-powder polish does not break down into powder particles and retains its uniformity in all traffic conditions. This is even more prevalent in winter where the dominance of FLOOR SEALER PLUS shows up even further against other polishes.
- High gloss, ultra durable, ultra high speed finish. Excellent presentation and response to UHS burnishing
- High anti-slip rating - 0.70 (Industry Standard 0.40). Increased safety and reduces risk of public liability claims.
- Urethane free. Easy to remove.
- Increased coverage. Covers more square meters of floor space.....coverage of up to 69 sq. meters per Litre.
- Self levelling. Provides a consistent and even coating across floor surfaces.
- Reduces Labour Cost. Easy to apply, repair and recoat. Extends recoat and strip-out cycles

Directions

Initial Application

Removal of the old finish (with MULTISTRIP) is desirable but not mandatory if the present floor coating is a hard metal interlock finish in good repair. Clean, scrub, or strip floor and rinse thoroughly with clean water and allow to dry. Apply one to three coats depending on porosity of the floor. Allow 20 to 30 minutes drying time between coats. Buffing at this point is not necessary to remove the gloss.

Future Maintenance

Periodic buffing, spray buffing or high speed burnishing may be used to repair and restore the gloss after the floor has been exposed to foot traffic.

Packages

2x5L

Revision Date: December 2013

Page 1 of 1